

VOC Content Test Certificate

Thursday November 1st, 2011

Manufacturer: Bostik NZ (19 Eastern Hutt Rd, New Zealand)

Sample Description: Bostik Firecaulk

Date Tested: November 2011 (Tested by FORAY Laboratories – NATA Accreditation 1231)

Test Method: SCAQMD Method 304-91 Determination of Volatile Organic Compounds (VOC) in Various Materials as referenced by South Coast Air Quality Management District (SCAQMD) Rule 1168

Test Data:

Specification Green Building Council of Australia Green Star Office Design V3 IEQ-13	Bostik Firecaulk
Architectural sealant 250 grams per Litre as VOC content per material	55 grams per Litre as VOC content per material



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Anne Saletti
BNanotech/BSc(Hons)
Consultant

CV111126